

Technical Data Sheet

EVAL™ F101B

32 mol% Ethylene-Vinyl Alcohol Copolymer

| Typical Properties | Unit | Test Method | Metric/(English) |
|--------------------|-----------------------------------|-------------------------|------------------|
| MFR | g/10min | ISO1133 (190°C, 2,160g) | 1.6 |
| Density | 10 ³ kg/m ³ | ISO1183-3 | 1.19 |

| Thermal Properties | Unit | Test Method | Metric/(English) |
|-----------------------------|---------|-------------|------------------|
| Melting Temperature | °C (°F) | ISO 11357 | 183 (361) |
| Crystallization Temperature | °C (°F) | ISO 11357 | 158 (316) |
| Glass Transition Point | °C (°F) | ISO 11357 | 60 (140) |
| Vicat Softening Point | °C (°F) | ISO 306 | 172 (342) |

| Mechanical Properties | Unit | Test Method (Dry injection piece, 23°C) | Metric/(English) |
|-------------------------|---------------------------------------------|--------------------------------------------|------------------|
| Tensile stress at break | MPa (psi) | ISO 527 | 34 (4,900) |
| Elongation at break | % | ISO 527 | 15 |
| Young's Modulus | GPa (psi) | ISO 527 | 4.5 (650,000) |
| Flexural Modulus | GPa (psi) | ISO 178 | 4.3 (620,000) |
| Charpy Impact Strength | kJ/m ² (ft.lbf/in ²) | ISO 179-1 | 8 (3.8) |
| Rockwell Hardness | HRM | ISO 2039-2 | 92 |

| Barrier Properties (cast film) | Unit | Test Method (Cast film, 20°C, 65%RH) | Metric/(English) |
|--------------------------------|-----------------------------------------------------------------------------------------------------|-----------------------------------------|------------------|
| Oxygen Transmission Rate | cm ³ .20µm/m ² .day.atm (cm ³ .mil/100in ² .day.atm) | ISO 21309-2 Annex C | 0.3 (0.015) |

Kuraray America, Inc.
2625 Bay Area Boulevard, Suite 600
Houston, TX 77058

Tel +1 800 423 9762
Fax +1 281 283 1722

www.evalevoh.com
www.kuraray.us.com

Data updated on: 2016-12-15
Layout updated on: 2020-07-21

The information contained here is, to the best of our knowledge, true and accurate. Actual performance may vary in particular applications. Because Kuraray cannot anticipate or control the many different conditions under which this product may be used, Kuraray does not guarantee the applicability or the accuracy of this information or the suitability of its products in any given situation. Kuraray accepts no liability for any loss or damage howsoever arising as a result of use or reliance on this information. All sales of this product are subject to Kuraray's Standard Terms and Conditions of Sale, a copy of which can be found on our website at:
<http://www.kuraray.us.com/standard-terms-and-conditions-of-sale/>.

Typical properties: These are not to be construed as specifications.